

100/140/250µm Multimode Optical Fiber

Product Information

Issue Date: 2005/5/10

This specification conforms to the requirement of IEC 60793 A1d.

Characteristics	Conditions	Specified Values	Unit
OPTICAL CHARACTERISTICS			
Attenuation Coefficient	850 nm	≤ 4.0	[dB/km]
	1300 nm	≤ 1.5	[dB/km]
Numerical Aperture		0.29 ± 0.015	
Bandwidth (*Higher bandwidth available upon request)	850 nm	≥ 150	[MHz·km]
	1300 nm	≥ 200	[MHz·km]
BACKSCATTER CHARACTERISTICS			
Attenuation Directional Uniformity		≤ 0.05	[dB/km]
Attenuation Uniformity		≤ 0.05	[dB]
Group Index of Refraction	850 nm	1.492	
	1300 nm	1.487	
PHYSICAL CHARACTERISTICS			
Core Diameter		100 ± 4	[µm]
Core Non- circularity		≤ 5	[%]
Core / Cladding Concentricity Error		≤ 3	[µm]
Cladding Diameter		140 ± 3	[µm]
Cladding Non-Circularity		≤ 2	[%]
Coating Diameter		245 ± 10	[µm]
Clad/Coat Concentricity Error		≤ 10	[µm]
Fiber curl		≥ 2	[m]
Proof Test		100	[kpsi]
Bend Induced Attenuation at 1300 nm (100 turns around a mandrel of 75 mm diameter)		≤ 0.5	[dB]
Average Coating Strip Force		≥ 1.3	[N]
Length (Typical)		1.1 ~ 8.8	[km]
ENVIRONMENTAL CHARACTERISTICS			
Temperature Dependence at 850 nm and 1300 nm Induced Attenuation – 60°C to +85°C		≤ 0.2	[dB/km]
Watersoak Dependence at 850 nm and 1300 nm Induced Attenuation at 20°C for 30 days		≤ 0.2	[dB/km]
Damp Heat Dependence at 850 nm and 1300 nm Induced Attenuation at 85°C, 85%R.H., 30 days		≤ 0.2	[dB/km]
Dynamic Tension Strength Median Tensile Strength of Unaged Fiber (0.5 m)		≥ 550	[Kpsi]
Dynamic Fatigue Constant (N_d)		20	

Prime Optical Fiber Corporation
 No.11, Ke Jung Rd.
 Science-Based Industrial Park
 Chu-Nan, 350, Miao-Li County, Taiwan, R.O.C.
 Tel: 886-37-586999 Fax: 886-37-586899
 E-mail: sales@pofc.com

