

62.5/125/250 μ m Multimode Optical Fiber

Product Information

Issue Date: 2004/5/25

This specification conforms to the requirement of IEC 60793 A1b and IEC 11801OM1.

OPTICAL CHARACTERISTICS

<i>Characteristics</i>	<i>Conditions</i>	<i>Specified Values</i>	<i>Unit</i>
Attenuation Coefficient	850 nm	≤ 3.0	[dB/km]
	1300 nm	≤ 0.8	[dB/km]
Numerical Aperture		0.275 ± 0.015	
Bandwidth (*Higher bandwidth available upon request)	850 nm	≥ 200	[MHz·km]
	1300 nm	≥ 500	[MHz·km]

BACKSCATTER CHARACTERISTICS

Attenuation Directional Uniformity		≤ 0.05	[dB/km]
Attenuation Uniformity		≤ 0.05	[dB]
Group Index of Refraction	850 nm	1.491	
	1300 nm	1.486	

PHYSICAL CHARACTERISTICS

Core Diameter		62.5 ± 3.0	[μ m]
Core Non- circularity		≤ 5	[%]
Core / Cladding Concentricity Error		≤ 3.0	[μ m]
Cladding Diameter		125 ± 1	[μ m]
Cladding Non-Circularity		≤ 2.0	[%]
Coating Diameter		245 ± 10	[μ m]
Clad/Coat Concentricity Error		≤ 6	[μ m]
Fiber curl		≤ 2	[m]
Proof Test		100	[kpsi]
Bend Induced Attenuation at 1300 nm (100 turns around a mandrel of 75 mm diameter)		≤ 0.5	[dB]
Coating Strip Force (Typical)		130	[g]
Length (Typical)		4.4 ~ 8.8	[km]

ENVIRONMENTAL CHARACTERISTICS

Temperature Dependence at 850 nm and 1300 nm Induced Attenuation – 60°C to +85°C		≤ 0.2	[dB/km]
Watersoak Dependence at 850 nm and 1300 nm Induced Attenuation at 20°C for 30 days		≤ 0.2	[dB/km]
Damp Heat Dependence at 850 nm and 1300 nm Induced Attenuation at 85°C, 85%R.H., 30 days		≤ 0.2	[dB/km]

Prime Optical Fiber Corporation
 No.11, Ke Jung Rd.
 Science-Based Industrial Park
 Chu-Nan, 350, Miao-Li County, Taiwan, R.O.C.
 Tel: 886-37-586999 Fax: 886-37-586899
 E-mail: sales@pofc.com.tw

